

CIFOMER ZRP

EPOXY ZINC RICH PRIMER

DESCRIPTION	THIS IS TWO-PACK, COLD CURED EPOXY/AMINE BASED ANTI-CORROSIVE PRIMER. IT IS
	COMPATIBLE WITH ALL EPOXY & PU TOP COATS. IT PROVIDES EFFICIENT PROTECTION FROM
DECOMMENDED LICE	CORROSION
RECOMMENDED USE	CAN BE USED ON ALL STEEL EXTERIOR AND INTERIOR AREAS WHERE EFFICIENT
	ANTICORROSION PROPERTIES ARE REQUIRED
PRODUCT SPECIFICATIONS	
COLOUR	GREY
FINISH	MATT - EGG SHELL
MIXING RATIO BY VOLUME	BASE: HARDENER 4:1
POT LIFE	AS PER RECOMMENDED COATING SYSTEM 6 TO 7 HOURS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
	24 DEGREES CENTIGRADE - ABEL APPARATUS
% VOLUME SOLIDS	45
RECOMMENDED DFT	40-50MICRONS
	9 TO 11 SQUARE METERS PER LITRE
	SURFACE DRY: 1/2HR TO 1 HR @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
	HARD DRY: 14 TO 16 HOURS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
	FULLY CURED: 7 DAYS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
` ,	8 HOURS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
. ,	7 DAYS
	REGULAR/ CONVENTIONAL SPRAY, AIRLESS SPRAY. BRUSHING ONLY FOR TOUCH UP
THINNER RECOMMENDED	EPOXY THINNER (CIFOMER EP THINNER)
SHELF LIFE SURFACE PREPARATION	12 MONTHS AS PER SUPPLIED PACKS: @ 30 DEGREES CENTIGRADE AND 65% REL.HUMIDITY
	REMOVE OIL, GREASE, RUST, DUST AND ANY OTHER FOREIGN MATTER BY SUITABLE MEANS
	AND BLAST CLEAN TO SA-2 AND 1/2 GRADE
	4. Use only when temperature is above 10 Degrees Centigrade
SAFETY PRECAUTIONS	Follow local and national safety rules
	2. Provide sufficient ventilation when working with solvent based coatings in confined areas
	3. In case of contamination, rinse with fresh running water and seek medical help immediately
	· · · · · · · · · · · · · · · · · · ·
NOTE	
DICCL AIMED	
DISCLAIMER	
	'
	OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS
	FOR PARTICULAR PURPOSE. Liability, if any, is limited to the replacement of the product or
	refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL
	DAMAGES ARE HEREBY EXCLUDED.
SAFETY PRECAUTIONS NOTE	 Stir well before and while painting MIX Base & Hardener thoroughly till homogenous mixture is formed. Leave for 5-10mins before use Use only when temperature is above 10 Degrees Centigrade Follow local and national safety rules Provide sufficient ventilation when working with solvent based coatings in confined areas In case of contamination, rinse with fresh running water and seek medical help immediately Keep the material away from heat, sparks and direct flame Practical coverage of paint depends on thinner consumption and loss factor depending on the site conditions Avoid inhallation of solvent vapours or paint mist by using facial mask, gloves and goggles Information giving here is in good faith without warranty the best of our knowledge, the technical data in our literature is true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to confirm to the specifications contained therein. WE MAKE NO OTHER WARRANTY OR GUARANTEE ANY KIND, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to the replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL