



RED OXIDE PRIMER

CIFOMER BMP (BASIC METAL PRIMER)

DESCRIPTION	IT IS A GENERAL PURPOSE PRIMER BASED ON ALKYD RESIN FORTIFIED WITH SPECIALISED RESINS.
RECOMMENDED USE	CAN BE USED IN MILD CORROSIVE, MARINE AND INDUSTRIAL ENVIRONMENT
PRODUCT SPECIFICATIONS	
COLOUR	RED OXIDE
FINISH	MATT - EGG SHELL
FLASH POINT	ABOVE 35 DEGREES CENTIGRADE - ABEL APPARATUS
% VOLUME SOLIDS	35
RECOMMENDED DFT	25 MICRONS
THEORETICAL COVERAGE	14 SQUARE METERS PER LITRE
DRYING TIME	SURFACE DRY: 30MINS TO 1 HOUR @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY HARD DRY: 6 TO 8 HOURS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
RECOATING INTERVAL (MIN)	12 HOURS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
RECOATING INTERVAL (MAX)	NONE
METHOD OF APPLICATION	BRUSH, AIRSPRAY, AIRLESS SPRAY
THINNER RECOMMENDED	GENERAL PURPOSE THINNER (CIFOMEL GP THINNER)
SHELF LIFE	12 MONTHS @ 30 DEGREES CENTIGRADE AND 65% RELATIVE HUMIDITY
SURFACE PREPARATION	NEW STEEL: ABRASIVE BLASTING OR POWER TOOL CLEANING TO SA-3 MAINTENANCE: REMOVE OIL, GREASE, RUST, DUST, LOOSE PAINT AND ANY OTHER FOREIGN MATTERS THOROUGHLY. 2. Stir well before and while painting 3. Another Film thickness can be applied than indicated depending on purpose and use. 4. Use only when temperature is above 10 Degrees Centigrade
SAFETY PRECAUTIONS	1. Follow local and national safety rules 2. Provide sufficient ventilation when working with solvent based coatings in confined areas 3. In case of contamination, rinse with fresh running water and seek medical help immediately 4. Keep the material away from heat, sparks and direct flame
NOTE	1. Practical coverage of paint depends on thinner consumption and loss factor depending on the site conditions 2. Avoid inhalation of solvent vapours or paint mist by using facial mask, gloves and goggles 3. Information giving here is in good faith without warranty
DISCLAIMER	To the best of our knowledge, the technical data in our literature is true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained therein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to the replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.